



MAKERS OF  ACUSHNET RUBBER  
O RINGS • SEAL RINGS • CUSTOM ELASTOMER SOLUTIONS

## Precix Compound Data Sheet

### Typical Physical Properties F13798 (F98) : Nanotube Semi-Conductive Fluorocarbon

#### Original Properties

#### Typical Values

Shore A Durometer	79
Tensile, MPa	13.0
Elongation, %	205
Color	Black

#### Electrical Properties

Volume Resistivity, ohm-cm	100
----------------------------	-----

#### Heat Age, 70 hrs @ 250°C

Change in Durometer, points	+3
Change in Tensile, %	-20.0
Change in Elongation, %	+20.5

#### Compression Set, 22 hrs @ 200°C

% Set	28.0
-------	------

#### Fluid Resistance, ASTM Fuel C, 70 hrs. @ R.T.

Change in Durometer	-2
Change in Tensile, %	-21.0
Change in Elongation, %	-1.5
Change in Volume, %	+ 2.7

#### Low Temperature Resistance

Brittleness @ -25°C	Pass
---------------------	------